




Heavy Duty Protective Coatings

LB-1625
V-Tech 325
Alkyd Dri-Mist Flat



Technical Data

PRODUCT DESCRIPTION

A fast-dry, lead free, alkyd flat finish formulated to be applied to interior structural steel surfaces where the overspray, or "fall out" must be dry before reaching the floor. VOC compliant.

INTENDED USES

Ideal for use on properly prepared bare structural steel or previously coated structural steel in sound condition.

PHYSICAL PROPERTIES

Color	White-Tintable to pastel colors.
Finish/Sheen	0 - 5 @ 85°
Resin Type	Alkyd
Clean-up Solvents	Diamond Vogel N-3023 Xylol
Solids By Weight	47%
Solids by Volume	24%
Light Reflectance (white)	83%
Theoretical Coverage**	385 ft ² /gal @ 1 mil
Dry Film Thickness / Coat	2 - 3 mils (37.5 - 50 microns)
Wet Film to Achieve DFT	8 - 12 mils (75 - 112.5 microns)
Coverage at DFT**	77 - 193 ft ² /gal @ 1.5 - 2 mils DFT
VOC's	3.33 lbs./gal. (400 grams/liter)
Thinning	DO NOT THIN

Drying Time* (hours) [ASTM D 1640] At 70°F (21°C) & 50% R.H.
 Minimum Fall - 10 feet
 Dry to Touch - 30 minutes
 Minimum Recoat - 2 - 4 hours

* Dry times vary with surface temperature, air movement, humidity and film thickness.
 ** Coverage rates are estimates based on the products volume solids and make no allowance for material loss during application. Actual spread rates may vary dependent on applicator experience, surface porosity and texture.

PERFORMANCE

Performance criteria meet or exceed Master Painter Institute (MPI) # 55 approval standards.

RECOMMENDED PRIMERS

Cote-All Primer (AZ-Series)
V-Cote 200 Acrylic Maintenance Primer/Finish (MC-Series)

SURFACE PREPARATION

All surfaces must be cured, clean, sound, dry and free of all dirt, dust, wax, oil, grease, chalk and any other contamination that would interfere with new coating adhesion. Bare surfaces must be properly prepared prior to application of this product.

Structural Steel Surfaces:

Remove loose rust and mill scale with hand or power abrading tools as per SSPC-SP-2 and SSPC-SP-3. Spot prime rusted areas with rust inhibitive primer.

Previously Painted Metal Surfaces:

Remove dirt and dust. Power or hand washing is recommended to remove contamination. If oil or grease is present, use of a cleaner/degreaser is required. All cleaning residue must be completely rinsed from the surface. Allow to dry. Remove all loose coatings, rust and corrosion by scraping, sanding or other abrading method as per SSPC-SP-2 and SSPC-SP-3. Use sandpaper to dull slick, glossy and/or non-porous surfaces with sandpaper. Spot prime bare and rusted areas.

Mildew:

Remove by using a solution of one part household bleach and three parts water. Apply to mildewed area and scrub. Allow solution to remain on the surface for 3 to 5 minutes and then rinse completely and allow to dry before coating application.

APPLICATION

Stir material prior to application. Any sediment that is in the bottom of the can must be thoroughly mixed in. Intermix tinted containers to ensure color uniformity of all material. Minimum surface and air temperature required for application is 50° F (10° C). A minimum fall of 10 feet and minimum temperature of 70° F (21° C) is required for optimum dry fall characteristics. Lower fall height and temperatures may result in overspray adhering to the floor. While this product is not subject to freezing, curing is affected by temperature, humidity and air movement. Cold temperatures will greatly increase drying time. Application at elevated temperatures, wind conditions and/or low humidity may require special application procedures to achieve proper film formation.

Dry fall characteristics will be adversely affected at temperatures below 70° F or above 50% relative humidity.

Airless Spray:

Flush airless lines with Diamond Vogel N3023 Xylol. Equipment must be clean prior to start. Apply the product in even coats and maintain a wet edge. Use multiple passes to achieve film build. One coat is usually sufficient however, if more than one coat is needed, allow 2 to 4 hours before recoating.

<i>Tip Orifice</i>	<i>Atomizing Pressure</i>	<i>Mat'l Hose ID</i>	<i>Manifold Filter</i>
0.013" to 0.015"	2500-3000 psi	1/4"	60 mesh

SAFETY PRECAUTIONS

Paint products contain chemical ingredients which are considered hazardous. Prior to use, read container label warnings and the current Material Safety Data Sheet for important health and safety information. Insure these instructions are practiced during product application and cure. **Keep out of the reach of children.**

LIMITED WARRANTY

The technical data and suggestions for use contained in this document are true and correct to the best of our knowledge at the date of issuance. The statements of this document do not constitute a warranty, expressed or implied, as to the performance of these products. Since Diamond Vogel Paints does not control the application of its products, or the condition of the surfaces to which they are applied, Diamond Vogel Paint's liability will under no circumstances exceed replacement of the product. **All technical information is subject to change without notice.**