

Nexgen® Industrial enamel

Diamond 😰 Vogeľ

IB-1563 3.5 ICS White Base Enamel W/B

Nexgen is a fast-drying, versatile, industrial finishing enamel for manufacturers of metal products.

夏季()))手中

Ideal for industrial OEM uses, including agricultural and construction equipment.

Diamond Vogel[®] Nexgen Industrial Enamel

The Nexgen Enamel system has been developed as a fast-drying, versatile, industrial finishing enamel for manufacturers of metal products. It offers a quick dry time, high gloss, and excellent color and gloss retention. Nexgen is ideal for industrial OEM uses, including agricultural and construction equipment.

FEATURES

- Quick dry time
- Excellent color retention
- High-gloss appearance
- Versatile across many markets

FIELD OF APPLICATION

Nexgen may be used for one-coat, direct-tometal applications; however, a primer is required for long-term corrosion protection. Primers should be tack-free before top coating. Nexgen may be spray or dip applied. IG-0267 Urethane Activator can be used from 6A:1B to 10A:1B for enhanced cure, gloss, abrasion resistance, and exterior durability. See data sheet for details.

PHYSICAL PROPERTIES

Weight Solids:	59% to 66%
Volume Solids:	48% to 52%
Resin Type:	Modified Alkyd
Gloss:	90+ at 60°
Theoretical Coverage:	770 to 840 sq. ft. at 1.0 mil
Weight Per Gallon:	9.0 to 11.0 pounds
Viscosity at 77°F:	#3 Zahn – 20 to 30 seconds

* For VOC information, see technical data sheet.





Diamond | INDUSTRIAL

1020 Albany Place SE • Orange City, IA 51041 (712) 737-4993 diamondvogel.com/industrial

The technical data and suggestions for use contained in this document are true and correct to the best of our knowledge at the date of issuance. The statements of this document do not constitute a warranty, expressed or implied, as to the performance of these products. Since Diamond Vogel does not control the application of its products or the condition of the surfaces to which they are applied, Diamond Vogel's liability will under no circumstances exceed replacement of the surfaces. All technical information is subject to change without notice.