


Peridium® T10 Super Durable TGIC Polyester Powder Coatings

Peridium T10 Powder Coatings offer excellent application and performance characteristics. Diamond Vogel's focus on tightly controlled particle size distribution promotes ideal first-pass transfer efficiency. Peridium T10 provides super weatherability, corrosion resistance, and chemical resistance in one superior coating. This coating provides the best balance between smoothness and edge coverage.

TYPICAL APPLICATIONS

- Agricultural equipment
- Recreational equipment
- Electrical enclosures
- Wheels and rims
- Construction equipment
- Lawn and garden equipment
- Patio furniture

CURE SCHEDULE



- Typical cure schedule 10 minutes @ 390°F
- Non-blooming

CURED FILM PROPERTIES

PCI Powder Smoothness Rating	6-7 (high gloss)
Specific Gravity (ASTM D792)	1.2 to 1.8
Adhesion (ASTM D3359)	5B (100%)
Gloss (ASTM D523)	55-99
Pencil Hardness (ASTM D3363)	3H+
Impact (ASTM D2794)	80-160 inch lbs
Flexibility (ASTM D522)	1/8 inch - No cracking
Humidity (ASTM D2247)	1,000+ hours
Salt Spray (ASTM B117)	2,500+ hours

**Film properties are dependent on gloss, pigmentation, film thickness, and cure temperature.*

STORAGE AND HANDLING

Diamond Vogel powder coatings should be stored at normal room temperature and humidity (less than 80°F and 50-60% RH). Shelf life will be approximately six months to over a year depending on storage conditions. Always rotate inventories to ensure trouble-free powder application. When storage conditions are not the same as the application area, allow a 24 hour acclimation period within the application area to prevent moisture condensation in the powder. Always protect virgin and reclaim powder from excessive heat and humidity.

INDUSTRIAL HYGIENE

Powder handling should always be done in conjunction with proper dust collection and personal protective equipment. Please refer to the Safety Data Sheet for more detailed information.