

## Peridium® T70


### Low Cure High Smoothness TGIC Polyester Powder Coatings

Peridium T70 Powder Coatings offer excellent application and performance characteristics. Diamond Vogel's focus on tightly controlled particle size distribution promotes ideal first-pass transfer efficiency. Peridium T70 has good exterior durability, very good smoothness, and overbake resistance. It also offers a wide cure window, ideal for parts with different metal thicknesses.

#### TYPICAL APPLICATIONS

- Agricultural equipment
- Recreational equipment
- Electrical enclosures
- Wheels and rims
- Construction equipment
- Lawn and garden equipment
- Appliances
- Lawn furniture

#### CURE SCHEDULE



- Typical cure schedule 10 minutes @ 320°F
- Blooming resistance down to 300°F
- Recommended for coating parts composed of mixed light and heavy gauge metal mass

#### CURED FILM PROPERTIES

PCI Powder Smoothness Rating	6 (high gloss)
Specific Gravity (ASTM D792)	1.2 to 1.8
Adhesion (ASTM D3359)	5B (100%)
Gloss (ASTM D523)	55-99
Pencil Hardness (ASTM D3363)	2H+
Impact (ASTM D2794)	up to 160 inch lbs
Flexibility (ASTM D522)	1/8 inch - No cracking
Humidity (ASTM D2247)	1,000+ hours
Salt Spray (ASTM B117)	1,000+ hours

*\*Film properties are dependent on gloss, pigmentation, film thickness, and cure temperature.*

#### STORAGE AND HANDLING

Diamond Vogel powder coatings should be stored at normal room temperature and humidity (less than 80°F and 50-60% RH). Shelf life will be approximately six months to over a year depending on storage conditions. Always rotate inventories to ensure trouble-free powder application. When storage conditions are not the same as the application area, allow a 24 hour acclimation period within the application area to prevent moisture condensation in the powder. Always protect virgin and reclaim powder from excessive heat and humidity.

#### INDUSTRIAL HYGIENE

Powder handling should always be done in conjunction with proper dust collection and personal protective equipment. Please refer to the Safety Data Sheet for more detailed information.