

**Product Data Sheet**

**PRODUCT DESCRIPTION**

DiaPro Block Filler is a quality acrylic latex block filler designed for interior or exterior use.

**TYPICAL USES**

Formulated for use on all types porous concrete and haydite cinder block on commercial and residential buildings. DiaPro Block Filler may be top coated with a variety of latex and solvent based finishes. **Not recommended for use in wet environments.**

**BASES & COLORS** (tintable with ACS Colorant)

BF-1515 White Up to 2 oz/gal

**PHYSICAL PROPERTIES**(BF-1515)

Resin Type	Acrylic Latex
Clean-up Solvent	Water
Finish	0-5 @ 85°
Solids by Weight	70 %
Solids by Volume	50 %

Recommended Dry Film Thickness per Coat 5-15 mils

Wet Film to Achieve DFT 10-30 mils

Theoretical Coverage @ 1 mil 802 ft<sup>2</sup>/gallon

Practical Coverage at Recommended DFT<sup>1</sup> 53-160 ft<sup>2</sup>/gallon

Dry Times<sup>2</sup>  
@ 70° F (21° C) and 50% R.H. Touch 2 hours  
Recoat 4 hours

VOCs <50 grams/liter

1 Spread rates are estimates based on products volume solids and make no allowance for material loss during application. Actual spread rates may vary dependent on applicator experience, surface porosity and texture.

2 Dry times may vary depending upon temperature, humidity and degree of air movement.

**SPECIFICATIONS**

**Exterior Porous Block/Haydite Cinder Block**

1 ct DiaPro Acrylic Block Filler  
2 cts Any B-Series Exterior Latex Finish  
or  
2 cts VersAcryl 222 Acrylic Maintenance S/G  
or  
2 cts Permaflex Elastomeric Finish

**Interior Porous Block**

1 ct DiaPro Acrylic Block Filler  
2 cts Any Diamond Vogel Interior Latex, Alkyd and most Epoxy Finishes.

This data sheet provides general recommendations and not intended to limit the use of this product. Test areas are always recommended to confirm results. For more detailed recommendations, please contact your local Diamond Vogel Sales Representative.

## SURFACE PREPARATION

All surfaces must be cured, clean, sound, dry and free of all dirt, dust, efflorescence, wax, oil, grease, chalk and any other contamination that would interfere with new coating adhesion. **Bare surfaces must be properly prepared prior to application of this product.**

### Block Surfaces

New masonry and mortar must cure for a *minimum* of 30 days at 72° F (22° C) prior to coating application. Level all surface projections and mortar spatters. Remove all soluble salts.

### Previously Painted Surfaces

- Power or hand washing is recommended to remove contamination. If oil or grease is present, use of a cleaner/degreaser is required. All cleaning residue must be completely rinsed from the surface. Allow to dry.
- Remove all loose coatings and corrosion by scraping, sanding or other abrading method. Use BF-1515 to fill exposed, rough surface area.
- Patch cracks and surface imperfections; sand and wipe clean.

### Mildew

Remove by using a solution of one (1) part household bleach to three (3) parts water. Apply to mildewed area and scrub. Allow solution to remain on the surface for 3 to 5 minutes then rinse completely and allow to dry before coating application. Do not add ammonia to the bleach/water solution.

## APPLICATION

- Stir material prior to application. Intermix tinted containers to ensure color uniformity of all material.
- Equipment must be clean prior to start. Flush airless lines with water.
- Apply by brush, roller or spray. A good quality synthetic brush will make application easier. Select a roller cover suited for the texture of the surface to be coated.
- Airless tip sizes of .021 to .035 are recommended; remove gun and pump filters to allow material to flow properly. Back roll after spraying.
- An airless spray pump size of one gallon per minute as a minimum is recommended.
- Apply the product in full even coats and maintain a wet edge. Allow the product to dry between coats.
- Do not thin.

## ENVIRONMENTAL VARIABLES

Protect product from freezing prior to and during application. Minimum surface and air temperature required for application is 50° F (10° C) and at least 5° F (3° C) above the dew point. Curing is affected by temperature, humidity and air movement. The minimums must be maintained for at least eight (8) hours in order to achieve proper film formation. Application at elevated temperatures, wind conditions, and/or low humidity may require special application procedures to achieve proper film formation.

## CLEAN-UP

Clean up spills immediately with soap and warm water. Clean hands and tools immediately after use with soap and warm water. After cleaning, flush spray equipment with mineral spirits to prevent rusting of the equipment.

## CAUTIONS

Do not apply below 50° F  
Not intended for use on floors  
Do not take internally  
Protect from freezing  
Use with adequate ventilation  
**KEEP OUT OF REACH OF CHILDREN**

**\*WARNING!** If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to [www.epa.gov/lead](http://www.epa.gov/lead).

### Limited Warranty

The technical data and suggestions for use contained in this document are true and correct to the best of our knowledge at the date of issuance. The statements of this document do not constitute a warranty, expressed or implied, as to the performance of these products. Since Diamond Vogel does not control the application of its products, or the condition of the surfaces to which they are applied, Diamond Vogel's liability will under no circumstances exceed replacement of the product.