

Peridium[®]

POWDER COATINGS

VOGEL
INDUSTRIAL COATINGS

Specific Gravity (g/cm ³)	Film Thickness															
	1 mil	1.2 mils	1.5 mils	1.8 mils	2 mils	2.2 mils	2.5 mils	2.8 mils	3 mils	4 mils	5 mils	6 mils	7 mils	8 mils	9 mils	10 mils
1.0	193.2	161.0	128.8	107.3	96.6	87.8	77.2	96.6	64.4	48.3	38.6	32.2	27.6	24.2	21.5	19.3
1.1	175.6	146.3	117.0	97.5	87.8	79.8	70.2	87.8	58.5	43.9	35.1	29.3	25.1	22.0	19.5	17.6
1.2	161.0	134.1	107.3	89.4	80.5	73.1	64.4	80.5	53.7	40.3	32.2	26.8	23.0	20.1	17.9	16.1
1.3	148.6	123.8	99.0	82.5	74.3	67.5	59.4	74.3	49.5	37.2	29.7	24.8	21.2	18.6	16.5	14.9
1.4	138.0	115.0	92.0	76.6	69.0	62.7	55.2	69.0	46.0	34.5	27.6	23.0	19.7	17.3	15.3	13.8
1.5	128.8	107.3	85.8	71.5	64.4	58.5	51.5	64.4	42.9	32.2	25.8	21.5	18.4	16.1	14.3	12.9
1.6	120.8	100.6	80.5	67.1	60.4	54.9	48.3	60.4	40.3	30.2	24.2	20.1	17.3	15.1	13.4	12.1
1.7	113.6	94.6	75.7	63.1	56.8	51.6	45.4	56.8	37.9	28.4	22.7	18.9	16.2	14.2	12.6	11.4
1.8	107.3	89.4	71.5	59.6	53.6	48.7	42.9	53.7	35.8	26.8	21.5	17.9	15.3	13.4	11.9	10.7
1.9	101.7	84.7	67.8	56.5	50.8	46.2	40.6	50.9	33.9	25.4	20.3	17.0	14.5	12.7	11.3	10.2
2.0	96.6	80.5	64.4	53.6	48.3	43.9	38.6	48.3	32.2	24.2	19.3	16.1	13.8	12.1	10.7	9.7
Tabular Values in ft²/lb																