

HYPERTHANE[®]431

HYPERFORMANCE URETHANE

DTM Acrylic Urethane

PRODUCT CODES: IG12-53312 – White Base | IG02-53313 – Clear Base

DESCRIPTION: The Hyperthane 431 ICS Polyurethane System is a two component, DTM polyurethane high-performance coating system designed for manufacturers that demand excellent gloss retention, hardness, mar, and chemical resistance. This is the system of choice for industrial finishers that desire excellent resistance to fading or chalking from exposure to sunlight and chemicals under splash and spill conditions. The Hyperthane 431 ICS Polyurethane System can be applied with conventional, airless, electrostatic, and plural component equipment. **This urethane can be used as a tough, direct-to-metal polyurethane.**

PHYSICAL PROPERTIES: Mixed

| | |
|-----------------------|-----------------------------------|
| Weight Solids: | 54%-63% |
| Volume Solids: | 44% to 48% |
| Resin Type: | Proprietary |
| Gloss: | 90 at 60° |
| Theoretical Coverage: | 710 to 750 square feet at 1.0 mil |
| Blended Viscosity: | #2 Zahn – 35-40 seconds at 77°F |
| Sag | 8-10 WFT |
| *EPA VOC: | 2.8 pounds per gallon |

SURFACE PREPARATION: The service expectancy of a coating is primarily dependent upon good surface preparation. The surface to be coated should be free of mill scale, rust, oil, and other contaminants, including salt deposits. The Hyperthane 431 ICS Polyurethane System may be applied over steel, aluminum, fiberglass, or galvanized steel. Due to inconsistencies in galvanizing, please check with your local Vogel Industrial representative for recommendations and substrate testing. The recommended primer to use with Hyperthane 431 ICS Polyurethane System is the Stratum two component urethane primer system.

| | |
|----------------------|----------------------------------------------------------------------------------------------------|
| Steel: | Bare steel areas should be treated with an iron phosphate conversion coating and adequate rinsing. |
| Aluminum/Galvanized: | Aluminum and galvanizing should be treated with appropriate metal cleaners and conditioners. |

ACTIVATION:

| | |
|----------------|---------------------------------------------------|
| Mixing Ratio: | 4A:1B by volume with IG-0267, IG-0268, or IG-0299 |
| Sweat-In Time: | None |
| Pot Life: | 1.5 to 3 hours at 77°F |

APPLICATION: This urethane can be sprayed with all types of application equipment.

| | |
|-------------------|------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| Airless: | For airless application no reduction is necessary. Airless tip sizes should be in the .011 to .015 range. Adjust pressures accordingly for best atomization and transfer efficiencies. Air-assist airless pressures will be in the 800 to 1000 pound range for fluid and 30 to 50 pound range for atomizing air. |
| Conventional Air: | For conventional air and electrostatic spray some reduction may be necessary. Use Butyl Acetate or Toluol for reducing purposes. Pressures are dependent upon the type of gun and fluid nozzle, but typically will be in the 45 to 60 pound range for proper atomization. |
| In-Line Heat: | In-line heat may be utilized up to 100°F to improve application. Caution must be exercised to turn heat down during breaks and shut downs to avoid locking up the paint lines due to decrease in pot life. |

HYPERTHANE[®]431

HYPERFORMANCE URETHANE

| | |
|----------------------------|---------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| Dry Film Thickness: | For best results, dry film thicknesses should be 1.0 to 2.0 mils above surface profile. This will require wet film thicknesses of about 3.0 to 4.0 mils. Apply in two medium build coats. |
| Conventional Air: | For conventional air and electrostatic spray some reduction may be necessary. Use N94-50232 Medium Speed Reducer, N-4005 Zero VOC reducer, or MAK. Pressures are dependent upon the type of gun and fluid nozzle, but typically will be in the 45 to 60-pound range for proper atomization. Pot pressure between 10-25 psi. |
| In-Line Heat: | In-line heat may be utilized up to 100°F to improve application. Caution must be exercised to turn heat down during breaks and shutdowns to avoid locking up the paint lines due to decrease in pot life. |
| DRY TIMES: | Hyperthane 431 ICS Polyurethane System will typically dry to handle in 4 to 5 hours. Dry hard times will be 24 hours. The Hyperthane 431 ICS Polyurethane System can be recoated at tack free and up to 48 hours. After 48 hours the Hyperthane 431 ICS Polyurethane System will need to be scuff sanded to ensure inter-coat adhesion. Force drying: 20 to 30 minutes at 160° to 180°F depending on metal thickness and mass. Recoating after force drying: Scuff sanding may be required to ensure inter-coat adhesion. |
| CLEAN UP: | Use ketones to flush application lines and equipment. |
| PERFORMANCE: | Typical, tested on B-1000 panels, direct to metal. |
| Accelerated Weathering: | 1155 hours – no change |
| Florida Exposure: | 1 year < 10% loss of gloss |
| Salt Spray DTM: | 500 hours < 1/4" creep |
| Salt Spray over: | ASTM B-117 – 1,000 hours < 3/16" creep |
| Chemical Resistance: | ASTM D1308 – 30 minute spot Diesel – Pass, no visible changes Ammonia – Pass Hydraulic Fluid – Pass 30 Weight Oil - Pass |
| Pencil Hardness: | ASTM D3363 Average F at 72 hours at 3.5 mils DFT Average 2H at 7 days at 1.0 mils DFT |
| Direct and Reverse Impact: | ASTM D2794 80+ inch pounds direct – 40+ inch pounds reverse |
| Gravelometer: | ASTM D3170 – SAE-J400 4A Rating - Excellent |
| SAFETY PRECAUTIONS: | Contains aliphatic polymeric isocyanate and MAK when blended. Avoid contact with skin. Vapor and spray mist harmful. Use proper respiratory protection, including positive air supplied respirators. Refer to SDS for specific information. All information subject to change without notice. |

*VOC varies - depending on color, composition and catalyst selection.
Specific Data Sheets and SDS available upon request.