



PRODUCT

Fire Lane Solvent Borne Zone Marking Paint

DESCRIPTION

Fire Lane is a fast-drying zone marking paint for delineating fire lanes at schools, hospitals, office buildings, and other public buildings. It can also be used on airport runways. Fire Lane may be applied to either concrete or asphalt surfaces by a variety of methods.

COLORS

Red TM55-44771

SURFACE PREPARATION

The surface to be coated must be free of any contaminant that will prevent the paint from adhering to the surface. Oil, grease, loose paint chips, gravel, salt films and curing membranes may all interfere with the adhesion of the coating. The surface should be swept clean of all loose contaminants. Visible stains of oils or dirt should be washed from the surface prior to coating. Slick or glossy surfaces, such as hard steel troweled concrete should be abraded to provide surface profile for the coating to adhere.

APPLICATION

Stir material prior to application. Equipment must be clean prior to start. Flush airless lines with Toluol. Apply with conventional or airless spray equipment. Small areas may be brushed or rolled. Apply 1 coat at a wet film thickness of 15 mils. Allow to dry 10 minutes before allowing traffic to drive over this coating. This coating has been successfully applied through a heated system up to temperatures of 140° F. Heating the coating will decrease the dry time, if surface temperatures, relative humidity, and air movement remain within the requirements for proper application. Material may be thinned with Toluol to a maximum of 1 pint per 5 gallons as required for application, though this may increase dry time.

ENVIRONMENTAL VARIABLES

Apply when air and surface temperatures are above 35° F. Lower surface and air temperatures will slow the speed of dry. Surface temperatures below 70° F and/or relative humidity greater than 80% may require longer curing times prior to bearing traffic.

CLEAN-UP

Clean up spills immediately with Toluol. Clean equipment immediately after use with Toluol. After cleaning, flush spray equipment with mineral spirits to prevent rusting of the equipment.

CAUTIONS

Do not freeze. Do not apply below 35° F. Do not take internally. Use with adequate ventilation. KEEP OUT OF THE REACH OF CHILDREN.

WARNING! If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and wet mop. Before you start, find out how to protect yourself and your family by contacting the national Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

PHYSICAL PROPERTIES

Table with 2 columns: Property Name and Value. Rows include Resin Type (Acrylic / Alkyd), Clean-Up Solvent (Toluol), Finish (Flat), Solids by Weight (72%), Solids by Volume (50%), VOCs (<450 g/L), Wet Film to Achieve DFT (15 mils), Practical Coverage at Recommended DFT (107 sq.ft./gallon), 4" Lines at 15 mils WFT (320 ft./gallon), and Dry Time at 70° F (21°C) and 50% Relative Humidity - Tack Free (<10 minutes).

Revised: August 27, 2018