



TRAFFIC COATINGS

PRODUCT DATA SHEET

PRODUCT

Blue Acrylic Solvent Borne Traffic Marking Paint

DESCRIPTION

A fast-drying acrylic solvent borne marking paint suitable for application for marking and striping driveways, parking lots, sidewalks, curbs, or airport runways. It may be applied to either concrete or asphalt surfaces.

COLORS

Blue TM77-52263

SURFACE PREPARATION

The surface to be coated must be free of any contaminant that will prevent the paint from adhering to the surface. Oil, grease, loose paint chips, gravel, salt films and curing membranes may all interfere with the adhesion of the coating. The surface should be swept clean of all loose contaminants. Visible stains of oils or dirt should be washed from the surface prior to coating. Slick or glossy surfaces, such as hard steel troweled concrete should be abraded to provide surface profile for the coating to adhere.

APPLICATION

Stir material prior to application. Equipment must be clean prior to start. Flush airless lines with Toluol. Apply with conventional or airless spray equipment. Small areas may be brushed or rolled. Apply 1 coat at a wet film thickness of 15 mils. Allow to dry 10 minutes before allowing traffic to drive over this coating. This coating has been successfully applied through a heated system up to temperatures of 140° F. Heating the coating will decrease the dry time, if surface temperatures, relative humidity, and air movement remain within the requirements for proper application. Material may be thinned with Acetone to a maximum of 1 pint per 5 gallons as required for application, though this may increase dry time.

ENVIRONMENTAL VARIABLES

Apply when air and surface temperatures are above 35° F. Lower surface and air temperatures will slow the speed of dry. Surface temperatures below 70° F and/or relative humidity greater than 80% may require longer curing times prior to bearing traffic.

CLEAN-UP

Clean up spills immediately with Acetone. Clean equipment immediately after use with Acetone. After cleaning, flush spray equipment with mineral spirits to prevent rusting of the equipment.

CAUTIONS

Do not freeze. Do not apply below 35° F. Do not take internally. Use with adequate ventilation. KEEP OUT OF THE REACH OF CHILDREN.

WARNING! If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and wet mop. Before you start, find out how to protect yourself and your family by contacting the national Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

PHYSICAL PROPERTIES

Resin Type	Acrylic
Clean-Up Solvent	Acetone
Finish	Flat
Solids by Weight	72%
Solids by Volume	52%
VOCs	<100 g/L
Wet Film to Achieve DFT	15 mils
Practical Coverage at Recommended DFT	107 sq.ft./gallon
4" Lines at 15 mils WFT	320 ft./gallon
Dry Time at 70° F (21°C) and 50% Relative Humidity - Tack Free	<10 minutes

Revised: July 21, 2021

Diamond Vogel | Traffic Coatings
1020 Albany Place SE • Orange City, IA 51041
Phone: (800) 72-VOGEL
traffic@diamondvogel.com
diamondvogel.com/traffic

Limited Warranty

The technical data and suggestions for use contained in this document are true and correct to the best of our knowledge at the date of issuance. The statements of this document do not constitute a warranty, expressed or implied, as to the performance of these products. Since Diamond Vogel does not control the application of its products, or the condition of the surfaces to which they are applied, Diamond Vogel's liability will under no circumstances exceed replacement of the product.