

**Diamond Vogel** 

# **WEATHER-** *plate*<sup>®</sup>



**EXTERIOR 100% ACRYLIC LATEX**

Designed for durability, performance, and value on  
both new construction and re-paint projects.

## LONG LASTING, SENSATIONAL RESULTS

### Weather-Plate 100% Acrylic Latex Exterior Finish

is a fantastic option for your exacting projects since it provides exceptional, long-term protection while being extremely easy to use. Weather-Plate releases from a brush quickly and effortlessly while still applying smoothly by airless spray making the resulting finish look amazing. Outstanding touch-up reduces frustrations at the close of the job, and enhanced flexibility guards against cracking and peeling minimizing call backs. Weather-Plate is perfect for both new and re-paint projects on numerous substrates.



PHYSICAL PROPERTIES	FLAT	SATIN
Finish	0-5 @ 85°	30-35 @ 85°
Resin Type	100% Acrylic	
Dry Time to Touch	30 to 120 minutes at 70°F and 50% Relative Humidity	
Dry Time to Recoat	2 to 4 Hours at 70°F and 50% Relative Humidity	
Recommended Dry Film Thickness per coat	1.5 to 2.0 mils	
Practical Coverage at Recommended DFT	276 to 363 ft <sup>2</sup> /gallon	
Solids by Volume	34%	
VOC	<100 g/L	<150 g/L



### OUR FAMILIES' COMMITMENT TO YOU

Our founder, Andrew Vogel decided that the only paint good enough for the barns and homes in the varied and often harsh Midwest climate was paint he perfected himself. So in 1926, from a modest "workshop laboratory," a paint company was born. Four generations, seven manufacturing facilities,

70 service centers, and millions of gallons of paint later, we are still as stubborn. We still insist on perfecting our own formulas, producing and distributing our own products, and servicing our customers with the kind of passion and commitment worthy of Andrew's name.



Diamond Vogel  
 T/800-72-VOGEL F/712-737-4998  
 1110 Albany Place SE Orange City, IA 51041  
[www.diamondvogel.com](http://www.diamondvogel.com)

The technical data and suggestions for use contained in this document are true and correct to the best of our knowledge at the date of issuance. The statements of this document do not constitute a warranty, expressed or implied, as to the performance of these products.