

## Product Data Sheet

### PRODUCT DESCRIPTION

PermAcryl Interior Eggshell is a premium quality interior latex enamel. It is formulated for superior washability and durability. PermAcryl Eggshell dries to a soft luster finish, is spatter resistant and has excellent hide.

### TYPICAL USES

Formulated for use on residential and commercial interior walls, ceilings, trim and doors. Designed as a finish coat for interior drywall, wood, plaster and masonry surfaces.

### BASES & COLORS-tintable with ACS Colorant

DE-1530 Cotton White	N/A
DE-1539 Pure White Base	0-4 oz/gal
DE-1531 White Base	0-4 oz/gal
DE-1532 Midtone Base	2-6 oz/gal
DE-1533 Deep Base	4-10 oz/gal
DE-0534 Neutral Base	4-14 oz/gal

### PHYSICAL PROPERTIES(DE-1530)

Resin Type	Acrylic Latex
Clean-up Solvent	Water
Finish	40-50 @ 85°
Solids by Weight	47 %
Solids by Volume	36 %
Recommended Dry Film Thickness per Coat	1.5-2 mils
Wet Film to Achieve DFT	4-5.5 mils
Theoretical Coverage @ 1 mil	580 ft <sup>2</sup> /gallon
Practical Coverage at Recommended DFT <sup>1</sup>	290-387 ft <sup>2</sup> /gallon
Dry Times <sup>2</sup> @ 70° F (21° C) and 50% R.H.	Touch 2-4 hour Recoat 4-6 hours
VOCs (range from 140-150 g/L depending on base)	140 grams/liter

<sup>1</sup> Spread rates are estimates based on products volume solids and make no allowance for material loss during application. Actual spread rates may vary dependent on applicator experience, surface porosity and texture.

<sup>2</sup> Dry times may vary depending upon temperature, humidity and degree of air movement.

### SPECIFICATIONS

#### Drywall

- 1 ct Any DU-Series Interior Latex Primers
- 2 cts PermAcryl Interior Eggshell

#### Plaster

- 1 ct Acryl Prime 100% Acrylic Primer/Sealer
- or
- 1 ct Alkyd Enamel Undercoat
- 2 cts PermAcryl Interior Eggshell

#### Ferrous Metal

- 1 ct Any CoteAll Multi-Purpose Primer
- or
- 1 ct Vers-Acryl 200 Acrylic Maintenance Primer
- 2 cts PermAcryl Interior Eggshell

#### Galvanized Metal:

- 1 ct Vers-Acryl 200 Acrylic Maintenance Primer
- 2 cts PermAcryl Interior Eggshell

#### Aluminum

- 1 ct Vers-Acryl 200 Acrylic Maintenance Primer
- 2 cts PermAcryl Interior Eggshell

#### Interior Wood

- 1 ct Mill Max Latex Enamel Undercoat
- or
- 1 ct Alkyd Enamel Undercoat
- 2 cts PermAcryl Interior Eggshell

#### Smooth Block

- 1 ct Acryl Prime 100% Acrylic Primer/Sealer
- 2 cts PermAcryl Interior Eggshell

#### Porous Block

- 1 ct Any BF-Series Block Fillers
- 2 cts PermAcryl Interior Eggshell

This data sheet provides general recommendations and not intended to limit the use of this product. Test areas are always recommended to confirm results. For more detailed recommendations, please contact your local Diamond Vogel Sales Representative.

## SURFACE PREPARATION

All surfaces must be cured, clean, sound, dry and free of all dirt, dust, efflorescence, wax, oil, grease, chalk and any other contamination that would interfere with new coating adhesion.

**Bare surfaces must be properly prepared and primed prior to application of this product.**

### Masonry Surfaces - Poured Concrete, Concrete Block

New concrete and mortar should cure for a *minimum* of 30 days at 72° F (22° C) prior to coating application. Level all surface projections and mortar spatters by stoning. Rake mortar joints clean and remove all soluble salts.

**Wood Surfaces** Sand smooth any exposed wood surfaces. Patch nail holes and any imperfections with wood filler or putty and sand smooth. Remove sanding dust.

**Plaster Surfaces** New plaster must cure for a *minimum* of 30 days at 72° F (22° C) prior to coating application. Sand smooth and dust. Fill cracks with spackling compound, allow to dry and sand smooth. Remove sanding dust.

**Drywall Surfaces** Fill nail holes and imperfections with spackling compound and allow to dry. Sand tape joints and spackled areas and remove dust. New drywall should be primed with an appropriate PVA primer or used as self-priming.

**New Galvanized/Aluminum Metal Surfaces** Solvent wipe to remove surface contamination, then use an etching solution or abrade the surface by sanding.

**Weathered Galvanized/Aluminum Surfaces** Power or hand wash with detergent and rinse thoroughly. The surface must be dull and slightly rough; use an etching solution or sand if needed.

**Ferrous Metal Surfaces** Remove loose rust and mill scale with hand or power abrading tools (reference SSPC-SP-2 or SSPC-SP-3).

### Previously Painted Surfaces

- Cleaning is recommended to remove contamination. If oil or grease is present, use of a cleaner/degreaser is required. All cleaning residue must be completely rinsed from the surface. Allow to dry.
- Remove all loose coatings and corrosion by scraping, sanding or other abrading method. Dull glossy, slick and/or non-porous surfaces with sandpaper.
- Patch and fill areas as needed. Spot prime bare areas with appropriate primer.

### Mildew

Remove by using a solution of one (1) part household bleach and three (3) parts water. Apply to mildewed area and scrub. Allow solution to remain on the surface for 3 to 5 minutes then rinse completely and allow to dry before coating application. Do not add ammonia to the bleach/water solution.

## APPLICATION

- Stir material prior to application. Intermit tinted containers to ensure color uniformity of all material.
- Equipment must be clean prior to start. Flush airless lines with clean water.
- Apply by brush, roller or spray. A good quality synthetic brush will make application easier. Select a roller cover suited for the texture of the surface to be coated. Airless tip sizes of .015 to .017 are recommended.
- Apply the product in full even coats and maintain a wet edge. Allow the product to dry between coats.
- Do not thin.

## ENVIRONMENTAL VARIABLES

Protect product from freezing prior to and during application. Minimum surface and air temperature required for application is 50° F (10° C) and at least 5° F (3° C) above the dew point. Curing is affected by temperature, humidity and air movement. The minimums must be maintained for at least eight (8) hours in order to achieve proper film formation. Application at elevated temperatures, wind conditions, and/or low humidity may require special application procedures to achieve proper film formation.

## CLEAN-UP

Clean up spills immediately with soap and warm water. Clean hands and tools immediately after use with soap and warm water. After cleaning, flush spray equipment with mineral spirits to prevent rusting of the equipment.

**Coating must be fully cured before attempting to wash the surface. Curing is temperature and humidity sensitive, ranging from 14 to 28 days.**

## CAUTIONS

For interior use only  
Not intended for use on floors  
Do not apply below 50° F.  
Protect from freezing  
Do not take internally  
Use with adequate ventilation  
**KEEP OUT OF REACH OF CHILDREN**

\*WARNING! If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to [www.epa.gov/lead](http://www.epa.gov/lead).

**Your Satisfaction Guaranteed** Diamond Vogel assures your complete satisfaction with the application, appearance and performance properties of this product if it is applied to a properly prepared surface in accordance with label instruction. If this paint fails to perform, Diamond Vogel will furnish an equivalent amount of new paint at no cost or will refund the purchase price upon proof of purchase. This warranty does not include labor or cost of labor for the application or removal of any paint. This warranty gives you specific legal rights, and you may also have other rights which vary from state to state.