

Product Data Sheet

PRODUCT DESCRIPTION

FastTurn Interior Latex Flat is designed for new construction and multi-family repaints where an economical finish system is required. FastTurn minimizes drywall imperfections with its absolute flat appearance that produces an appealing, even surface, and it makes for an outstanding base coat for subsequent finishes. FastTurn's terrific touch-up qualities reduces labor costs and frustrations on the job site. FastTurn allows you to cover it quick and make it look great.

TYPICAL USES

Formulated for use as a finish coat on residential or commercial interior surfaces constructed of plaster, wallboard or wood.

BASES & COLORS-tintable with ACS Colorant

DF-1620 White 0–2 oz/gal

PHYSICAL PROPERTIES(DF-1620)

Resin Type	Vinyl Acrylic
Clean-up Solvent	Water
Finish	0–5 @ 85°
Solids by Weight	59%
Solids by Volume	39%
Recommended Dry Film Thickness per Coat	3.0–4.0 mils
Wet Film to Achieve DFT	7.7–10.3 mils
Theoretical Coverage @ 1 mil	626 ft ² /gallon
Practical Coverage at Recommended DFT ¹	157–209 ft ² /gallon
<u>Dry Times</u> ² @ 70° F (21° C) and 50% R.H.	Touch 1 to 2 hours Recoat 4 hours
VOCs	47 grams/liter

1 Spread rates are estimates based on products volume solids and make no allowance for material loss during application. Actual spread rates may vary dependent on applicator experience, surface porosity and texture.

2 Dry times may vary depending upon temperature, humidity and degree of air movement.

SPECIFICATIONS

Drywall

1 ct Any Diamond Vogel Interior Latex Primer
2 cts FastTurn Interior Flat
or
2 cts FastTurn Interior Flat as self priming

Plaster

1 ct Omni-Prep Universal Interior Primer
2 cts FastTurn Interior Flat

Interior Wood

1 ct Mill Max Latex Enamel Undercoat
2 cts FastTurn Interior Flat

This data sheet provides general recommendations and not intended to limit the use of this product. Test areas are always recommended to confirm results. For more detailed recommendations, please contact your local Diamond Vogel Sales Representative

SURFACE PREPARATION

All surfaces must be cured, clean, sound, dry and free of all dirt, dust, efflorescence, wax, oil, grease, chalk and any other contamination that would interfere with new coating adhesion.

Bare surfaces must be properly prepared prior to application of this product.

Wood Surfaces Sand smooth any exposed wood surfaces. Patch nail holes and any imperfections with wood filler or putty and sand smooth. Remove sanding dust and apply appropriate primer

Plaster Surfaces New plaster must cure for a *minimum* of 30 days at 72° F (22° C) prior to coating application. Sand smooth and dust. Fill cracks with spackling compound, allow to dry and sand smooth. Remove sanding dust and apply appropriate primer.

Drywall Surfaces Fill nail holes and imperfections with spackling compound and allow to dry. Sand tape joints and spackled areas and remove dust. New drywall should be primed with an appropriate primer or used as self-priming.

Previously Painted Surfaces

- Cleaning is recommended to remove contamination. If oil or grease is present, use of a cleaner/degreaser is required. All cleaning residue must be completely rinsed from the surface. Allow to dry.
- Remove all loose coatings and corrosion by scraping, sanding or other abrading method. Dull glossy, slick and/or non-porous surfaces with sandpaper.
- Patch and fill areas as needed. Spot prime bare areas with appropriate primer.

Mildew

Remove by using a solution of one (1) part household bleach and three (3) parts water. Apply to mildewed area and scrub. Allow solution to remain on the surface for 3 to 5 minutes then rinse completely and allow to dry before coating application. Do not add ammonia to the bleach/water solution.

APPLICATION

- Stir material prior to application. Intermix tinted containers to ensure color uniformity of all material.
- Equipment must be clean prior to start. Flush airless lines with clean water.
- Apply by brush, roller or spray. A good quality synthetic brush will make application easier. Select a roller cover suited for the texture of the surface to be coated. Airless tip sizes of .015 to .021 are recommended.
- Apply the product in full even coats and maintain a wet edge. Allow the product to dry between coats.
- Do not thin.

ENVIRONMENTAL VARIABLES

Protect product from freezing prior to and during application. Minimum surface and air temperature required for application is 50° F (10° C) and at least 5° F (3° C) above the dew point. Curing is affected by temperature, humidity and air movement. The minimums must be maintained for at least eight (8) hours in order to achieve proper film formation. Application at elevated temperatures, wind conditions, and/or low humidity may require special application procedures to achieve proper film formation.

CLEAN-UP

Clean up spills immediately with soap and warm water. Clean hands and tools immediately after use with soap and warm water. After cleaning, flush spray equipment with mineral spirits to prevent rusting of the equipment.

CAUTIONS

For interior use only
Not intended for use on floors
Do not apply below 50° F.
Protect from freezing
Do not take internally
Use with adequate ventilation
KEEP OUT OF REACH OF CHILDREN

*WARNING! If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH-approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and wet mop. Before you start, find out how to protect yourself and your family by contacting the National Lead Information Hotline at 1-800-424-LEAD or log on to www.epa.gov/lead.

Limited Warranty

The technical data and suggestions for use contained in this document are true and correct to the best of our knowledge at the date of issuance. The statements of this document do not constitute a warranty, expressed or implied, as to the performance of these products. Since Diamond Vogel does not control the application of its products, or the condition of the surfaces to which they are applied, Diamond Vogel's liability will under no circumstances exceed replacement of the product.